



# BISON KIT®

## SUPER STRONG, LIQUID, UNIVERSAL CONTACT ADHESIVE.



### PRODUCT DESCRIPTION

Super-strong universal contact adhesive based on neoprene rubber. For innumerable repair and DIY jobs that require immediate bonding. Extremely suitable for materials under strain. Moisture and frost proof. Resistant to temperatures between -40°C and +70°C.

### FIELD OF APPLICATION

Ideally suited for surface bonding or laminating of many materials that require immediate bonding, loading or processing. Bonds wood, board, veneer, plastic and metal panel boards (HPL, Formica®, for example), (foam) rubber, leather, cork, canvas, linoleum and polyether foam (sound insulation), among other things, to itself as well as to many other surfaces. Also for repairing shoes, bags, toys and carpets, or for doing (hobby) handicraft work. Not suitable for polystyrene foam (Tempex®), PE, PP and vinyl.

### PROPERTIES

- Bonds immediately
- Super-strong
- Suitable for materials under stress
- Universal
- Liquid
- Moisture and frost resistant
- Simple to use
- Resistant to temperatures between -40°C and +70°C

### PREPARATION

**Working conditions:** Use adhesive and parts to be bonded at room temperature only. The relative humidity must be below 65%. This is to avoid formation of bubbles in the final product. Once attached, adjustment is no longer possible. Always test on an (inconspicuous) part of the surface first.

**Surface requirements:** Surfaces must be dry, clean, dust- and grease-free and a good fit. Clean and degrease the surfaces to be bonded for optimal results.

**Preliminary surface treatment:** For optimal result, degrease first.

**Tools:** Use a solid brush or fine-toothed (1 mm) glue spreader to cover large surfaces. Use a roller or rubber mallet to join the materials firmly.

### APPLICATION

**Coverage:** 2-2.5 m<sup>2</sup>/litre, applied on both sides, depending on the nature of the materials to be bonded.

#### Directions for use:

Stir well before use. Should preferably not be diluted. Parts must be clean, dry and free of grease. Coat both substrates completely. Allow to dry for a minimum of 10-40 minutes. In case of porous materials, apply a second coat and let dry. Then join parts and roll or tap firmly (with a rubber mallet).

**Stains/residue:** Remove wet adhesive residue immediately with Degreaser/Thinner for Bison Kit®. Dried excess adhesive can only be removed mechanically or with a paint stripper (pre-test).

**Points of attention:** For optimum results, both the adhesive and the parts to be bonded must be at room temperature (definitely do not use below +10°C). The final bonding strength depends on the pressure applied. Therefore, press as firmly as possible across the entire surface. Should the adhesive joint between porous materials be exposed to long-lasting contact with water, the adhesive may detach from the wet surface.

### TECHNICAL PROPERTIES

**Moisture resistance:** Good

**Elasticity:** Very good

### TECHNICAL SPECIFICATIONS

**Viscosity:** approx. Liquid

**Solid matter:** approx. 24 %

**Density:** approx. 0.86 g/cm<sup>3</sup>

**Flash point:** K1 (<21°C)

### STORAGE CONDITIONS

At least 24 months after date of manufacture. Broken packaging limits storage life. Store properly closed in a cool and frost-free place. Shelf life is a minimum 24 months.